

Randy's Clear glaze Recipe

You need about 10kg to fill a 5 gallon bucket. I would suggest you try a test first. I've been testing a similar clear base from "mastering cone 6 glazes" ;

Materials	Amt
PPS Fusion Frit F-12	25.00
PPS Feldspar Custer Potash	22.00
PPS EPK	18.00
PPS Silica 295 mesh	26.00
PPS Talc Silverline 303	5.00
PPS Whiting (Calcium Carbonate)	<u>4.00</u>
Total:	100.00

I've modified it to change from frit 3134 to f-12 as 3134 may be very difficult to get in the future.

For every 100gm of dry materials start with 85 gm of water.

Date April 1 2024 - Will be setting up a small batch first as Randy suggests.

Revision #3

Created 1 April 2024 12:57:41 by Don

Updated 17 May 2025 21:19:02 by Don