

Randy's Clear glaze Recipe

You need about 10kg to fill a 5 gallon bucket. I would suggest you try a test first. I've been testing a similar clear base from "mastering cone 6 glazes" ;

| Materials | Amt |
|---------------------------------|-------------|
| PPS Fusion Frit F-12 | 25.00 |
| PPS Feldspar Custer Potash | 22.00 |
| PPS EPK | 18.00 |
| PPS Silica 295 mesh | 26.00 |
| PPS Talc Silverline 303 | 5.00 |
| PPS Whiting (Calcium Carbonate) | <u>4.00</u> |
| Total: | 100.00 |

I've modified it to change from frit 3134 to f-12 as 3134 may be very difficult to get in the future.

For every 100gm of dry materials start with 85 gm of water.

Date April 1 2024 - Will be setting up a small batch first as Randy suggests.

Revision #3

Created 1 April 2024 12:57:41 by Don

Updated 1 April 2024 14:01:50 by Don